

# Meyer Burger White

# 380 – 400 Wp

For higher energy yield over the same area: Heterojunction high-performance solar module with SmartWire Connection Technology (SWCT<sup>™</sup>).



#### Made in Germany. Designed in Switzerland.

Production and development according to the highest quality standards.



## Highly profitable

More energy yield over the same area even on cloudy or hot days.



#### **Extremely durable**

Outstanding cell stability and high breakage resistance thanks to patented SmartWire Connection Technology.



#### **Consistently sustainable**

Regional value creation, made without lead and produced using 100 % renewable energy.



 $\overline{X}$ 


#### **Guaranteed reliability**

Industry-leading 25-year product and performance warranty.

#### Extremely aesthetic

Elegant Swiss design suitable for all roof shapes and sophisticated architecture.









esidential rooftop

Commercial rooftop





8x3.5 (8x) Draina

holes

Ø4.5 (8x) Grounding holes 1

> Ø9 (4x) Mounting holes

Dimension in mm

Made in Germany. Designed in Switzerland.

> 1041 989

(Distance between mounting and grounding holes)

1200

Cable length



26

115

320

nounting holes)

(Distance be

1767 1127 ween

12

115

#### **Mechanical specification**

1767 x 1041 x 35
19.7
Tempered solar glass, 3.2 mm, with anti-reflective surface
White water-barrier backsheet
Black anodized aluminum
120 half-cells, mono n-Si, HJT with SWCT™ bifacial cell technology
3 diodes, IP68 rated in accordance with IEC 62790
PV cable 4 mm², 1.2 m length in accordance with EN 50618
1: MC4; 2: MC4-Evo2; 3: UKT Energy PV-CO02; 4: TE Connectivity PV4-S1 in accordance with IEC 62852, IP68 rated only when connected

#### Packages



Delivery by container or truck. For truck freight, 0.78 loading meters per pallet and stacking factor 2 apply.

#### **Electrical specification**<sup>1</sup>

Efficiency	Powe	er <sup>*</sup>	Short cire	cuit current	Open cir	cuit voltage	Cur	rent	Vol	tage
η	P <sub>max</sub>			I <sub>sc</sub>	,	V <sub>oc</sub>	I,	ipp	V	/ mpp
[%]	[W]			[A]		[V]	[4	4]		[V]
STC <sup>2</sup>	NMOT <sup>3</sup>	STC	NMOT	STC	NMOT	STC	NMOT	STC	NMOT	STC
20.7	287	380	8.7	10.8	42.1	44.4	8.1	10.2	35.2	37.3
20.9	290	385	8.7	10.8	42.1	44.4	8.2	10.2	35.5	37.6
21.2	294	390	8.7	10.8	42.2	44.5	8.2	10.3	35.9	37.9
21.5	298	395	8.7	10.9	42.3	44.5	8.2	10.3	36.2	38.3
21.7	302	400	8.7	10.9	42.3	44.6	8.3	10.4	36.5	38.6
	η [%] STC <sup>2</sup> 20.7 20.9 21.2 21.5	η P <sub>max</sub> [%] [W]   STC <sup>2</sup> NMOT <sup>3</sup> 20.7 287   20.9 290   21.2 294   21.5 298	n P <sub>max</sub> [%] [W]   STC <sup>2</sup> NMOT <sup>3</sup> STC   20.7 287 380   20.9 290 385   21.2 294 390   21.5 298 395	n Pmax   [%] [W]   STC <sup>2</sup> NMOT <sup>3</sup> STC NMOT   20.7 287 380 8.7   20.9 290 385 8.7   21.2 294 390 8.7   21.5 298 395 8.7	η P <sub>max</sub> I <sub>sc</sub> [%] [W] [A]   STC <sup>2</sup> NMOT <sup>3</sup> STC NMOT STC   20.7 287 380 8.7 10.8   20.9 290 385 8.7 10.8   21.2 294 390 8.7 10.8   21.5 298 395 8.7 10.9	η P <sub>max</sub> I <sub>sc</sub> N   [%] [W] [A] [M] <td>n P<sub>max</sub> I<sub>sc</sub> V<sub>oc</sub>   [%] [W] [A] [V]   STC<sup>2</sup> NMOT<sup>3</sup> STC NMOT STC NMOT   20.7 287 380 8.7 10.8 42.1 44.4   20.9 290 385 8.7 10.8 42.2 44.5   21.2 294 390 8.7 10.8 42.2 44.5   21.5 298 395 8.7 10.9 42.3 44.5</td> <td><math display="block">\begin{array}{c c c c c c c c c c c c c c c c c c c </math></td> <td><math display="block">\begin{tabular}{ c c c c c c c } \hline \$n\$ &amp; \$P_{max}\$ &amp; \$I_{sc}\$ &amp; \$V_{cc}\$ &amp; \$I_{mpp}\$ \\ \hline \$n\$ &amp; \$P_{max}\$ &amp; \$I_{sc}\$ &amp; \$V_{cc}\$ &amp; \$I_{mpp}\$ \\ \hline \$n\$ &amp; \$[N]\$ &amp; \$[M]\$ &amp;</math></td> <td><math display="block"> \begin{array}{c c c c c c c c c c c c c c c c c c c </math></td>	n P <sub>max</sub> I <sub>sc</sub> V <sub>oc</sub> [%] [W] [A] [V]   STC <sup>2</sup> NMOT <sup>3</sup> STC NMOT STC NMOT   20.7 287 380 8.7 10.8 42.1 44.4   20.9 290 385 8.7 10.8 42.2 44.5   21.2 294 390 8.7 10.8 42.2 44.5   21.5 298 395 8.7 10.9 42.3 44.5	$\begin{array}{c c c c c c c c c c c c c c c c c c c $	$\begin{tabular}{ c c c c c c c } \hline $n$ & $P_{max}$ & $I_{sc}$ & $V_{cc}$ & $I_{mpp}$ \\ \hline $n$ & $P_{max}$ & $I_{sc}$ & $V_{cc}$ & $I_{mpp}$ \\ \hline $n$ & $[N]$ & $[M]$ &$	$ \begin{array}{c c c c c c c c c c c c c c c c c c c $

\* (Power tolerance -0 W / +5 W for STC)

#### Temperature coefficients

Temperature coefficient of I <sub>sc</sub>	α	[%/K]	+0.033
Temperature coefficient of V <sub>oc</sub>	β	[%/K]	-0.234
Temperature coefficient of P <sub>MPP</sub>	γ	[%/K]	-0.259
Nominal Module Operating Temperature	NMOT <sup>3</sup>	[°C]	44±2

## Properties for system design

[V]	1000
[A]	20
[Pa]	6000/4000
[Pa]	4000/2666
	II
	1
	E/B2 /B <sub>ROOF</sub> (t1)
[°C]	-40 to +85
	[A] [Pa] [Pa]

#### **Certificates**

#### Certification


IEC 61215:2016, IEC 61730:2016, UL 61730-1, UL 61730-2, PID (IEC 62804), Salt Mist (IEC 61701)

Notice: All data and specifications are preliminary and subject to change without notice. For installation and operating instruction, please refer to installation guide, version 1.0.5\_UL Visit us at meyerburger.com

#### I-V curves at different irradiations



# Meyer Burger warranty



#### Test procedure according to IEC standard



<sup>1</sup>Measurement according to IEC 60904-3, measurement tolerance: ±3% \*STC: Irradiance 1000 W/m<sup>2</sup>, module temperature 25°C, ANLSG Spectrum NMOT: Nominal Module Operating Temperature, unit incadiance 800 W/m<sup>2</sup>, AMLSG spectrum, ambient temperature 20°C



Asof: I