

SLA-M Monocrystalline















320 Wp 60 Cell

Monocrystalline PV Module

(Available Early 2019)















100% MAXIMUM POWER DENSITY

Silfab's SLA-M 320 ultra-high-efficiency modules are optimized for both Residential and Commercial projects where maximum power density is preferred.

100% NORTH AMERICAN OUALITY MATTERS

Silfab's fully-automated manufacturing facility ensures precision engineering is applied at every stage. Superior reliability and performance combine to produce one of the highest quality modules with the lowest defect rate in the industry.

NORTH AMERICAN CUSTOMIZED SERVICE

Silfab's 100% North American based team leverages just-in-time manufacturing to deliver unparalleled service, on-time delivery and flexible project solutions.



ENSURES MAXIMUM EFFICIENCY

60 of the highest efficiency, premium quality monocrystalline cells result in a maximum power rating of 320Wp.

ADVANCED PERFORMANCE WARRANTY

30-year linear power performance guarantee

ENHANCED PRODUCT WARRANTY

25-year product workmanship warranty*

BUILT BY INDUSTRY EXPERTS

With over 35 years of industry experience, Silfab's technical team are pioneers in PV technology and are dedicated to an innovative approach that provides superior manufacturing processes including: infra-red cell sorting, glass washing, automated soldering and meticulous cell alignment.

POSITIVE TOLERANCE

(-0/+5W) All positive module sorting ensures maximum performance

III LOWEST DEFECT RATE*

Total automation ensures strict quality control during each step of the process at our certified ISO manufacturing facility. *82.56 ppm as per December 2017

LIGHT AND DURABLE

Engineered to accommodate low load bearing structures, while boasting up to 5400 Pa snow load capabilities. Lightweight frame is exclusively designed with wide-ranging racking compatibility and durability in mind.

PID RESISTANT

PID Resistant due to advanced cell technology and material selection. In accordance to IEC 62804-1

AVAILABLE WITH

Black Frame and Backsheet

Electrical Specifications		SILFAB SLA Monocrystalline	
Test Conditions		STC	NOCT
Module Power (Pmax)	Wp	320	242
Maximum power voltage (Vpmax)	V	33.7	30.3
Maximum power current (Ipmax)	Α	9.5	8.0
Open circuit voltage (Voc)	V	40.45	37.42
Short circuit current (Isc)	Α	9.96	8.17
Module efficiency	%	19.6	18.5
Maximum system voltage (VDC)	V	1000	
Series fuse rating	Α	20	
Power Tolerance	Wp	-0/+5	

 $Measurement \ conditions: \ STC\ 1000\ W/m2 \cdot AM\ 1.5 \cdot Temperature\ 25\ ^{\circ}C \cdot NOCT\ 800\ W/m^2 \cdot AM\ 1.5 \cdot Measurement \ uncertainty \leq 3\% \cdot Month \ 1.5 \cdot Measurement \ uncertainty \leq 3\% \cdot Month \ 1.5 \cdot Measurement \ uncertainty \leq 3\% \cdot Month \ 1.5 \cdot Measurement \ uncertainty \leq 3\% \cdot Month \ 1.5 \cdot Measurement \ uncertainty \leq 3\% \cdot Month \ 1.5 \cdot Measurement \ uncertainty \leq 3\% \cdot Month \ 1.5 \cdot Measurement \ uncertainty \leq 3\% \cdot Month \ 1.5 \cdot Measurement \ 1.5 \cdot Measu$ • Sun simulator calibration reference modules from Fraunhofer Institute. Electrical characteristics may vary by ±5% and power by -0/+5W.

Temperature Ratings		SILFAB SLA Monocrystalline	
Temperature Coefficient Isc	%/K	0.03	
Temperature Coefficient Voc	%/K	-0.30	
Temperature Coefficient Pmax	%/K	-0.38	
NOCT (± 2°C)	°C	45	
Operating temperature	°C	-40/+85	
Mechanical Properties and Components		SILFAB SLA Monocrystalline	
Module weight (± 1 kg)	kg	19	
Dimensions (H x L x D; ± 1mm)	mm	1650 x 990 x 38	
Maximum surface load (wind/snow)*	N/m ²	5400	
Hail impact resistance		ø 25 mm at 83 km/h	
Cells		60 - Si monocrystalline - 5 busbar - 156.75 x 156.75 mm	
Glass		3.2 mm high transmittance, tempered, antireflective coating	
Backsheet		Multilayer polyester-based	
Frame	Anodized Al (Black)		
Bypass diodes		3 diodes, 20SQ040 (45V/20A) IP67/IP68 Junction Box	
Cables and connectors (See installation manual)		1200 mm ø 5.7 mm (4 mm2), MC4 compatible	
Warranties		SILFAB SLA Monocrystalline	
Module product workmanship warranty		25 years*	
Linear power performance guarantee		30 years	

Certifications

SILFAB SLA Monocrystalline

ULC ORD C1703, UL 1703, IEC 61215, IEC 61730-1 and IEC 61730-2 Certified. FSEC and CEC listed. IEC 62716 Ammonia Corrosion, IEC 61701:2011 Salt Mist Corrosion Certified

UL Fire Rating: Type 2 (Type 1 on request) ISO9001:2015

Factory


Product

Warning: Read the installation and User Manual before handling, installing and operating modules.

Third-party generated pan files from Fraunhofer-Institute for Solar Energy Systems ISE are available for download at: www.silfabsolar.com/downloads



■ Pallets Per Truck: 36





Silfab Solar Inc. 240 Courtneypark Drive East Mississauga ON L5T 2Y3 Canada Tel +1 905-255-2501 | Fax +1 905-696-0267 info@silfabsolar.com | www.silfabsolar.com



Silfab Solar Inc. 800 Cornwall Ave Bellingham WA 98225 USA Tel +1 360-569-4733

